



BLUSH WITH MICROSLIP 519

<u>Product Name</u>	<u>INCI Name</u>	<u>%W/W</u>	<u>Supplier</u>
Phase A			
Rose Talc	Talc	61.55	Presperse LLC
Sericite PHN	Mica	15.00	Presperse LLC
Microslip 519	PTFE	2.00	Micro Powders, Inc.
Pearl II	Bismuth Oxychloride	4.00	Presperse LLC
Spheron® P-1500	Silica	0.50	Presperse LLC
Red Iron Oxide 7080	Iron Oxide	4.00	Warner Jenkinson
D&C Red No. 30 Lake	D&C Red No. 30 (&) Talc	2.00	N/A
Methylparaben, USP	Methylparaben	0.20	ISP
Propylparaben, USP	Propylparaben	0.20	ISP
Germall 115	Imidazolidinyl Urea	0.05	ISP
Zinc Laurate Z-12	Zinc Laurate	4.00	Ikeda
Phase B			
Permethyl® 102A	Isoeicosane	2.00	Presperse LLC
Permethyl® 104A	Polyisobutene	2.00	Presperse LLC
Crill 6	Sorbitan Isostearate	0.50	Croda

Procedure

1. Combine ingredients of Phase A.
2. Mix well using a ribbon type blender.
3. Pass through a micropulverizer until uniformly pulverized.
4. Pre-mix Phase B ingredients, then spray into Phase A.
5. Mix well until the color of the mixtures is uniformly blended.
6. Press at 1500 psi in an appropriate container.