



LOOSE FACE POWDER WITH MICROPOLY 250S

| <u>Product Name</u> | <u>INCI Name</u> | <u>%W/W</u> | <u>Supplier</u> |
|------------------------------|-------------------------------------|-------------|----------------------------|
| Phase A | | | |
| Sericite PHN | Mica | 90.39 | Presperse LLC |
| SM-1000 | Mica (&) Silica | 5.00 | Presperse LLC |
| SP-29 UVS | Bismuth Oxychloride/ Silica/Mica | 1.00 | Presperse LLC |
| Micropoly 250S | | | |
| Yellow Iron Oxide 7055 | Polyethylene | 2.00 | Micro Powders, Inc. |
| Red Iron Oxide 7080 | Iron Oxide | 0.25 | Warner Jenkinson |
| Brown Iron Oxide C33-5136 | Iron Oxide | 0.25 | Warner Jenkinson |
| Black Iron Oxide 7133 | Iron Oxide | 0.04 | Sun Chemical |
| Methylparaben, USP | Iron Oxide | 0.02 | Warner Jenkinson |
| Propylparaben, USP | Methylparaben | 0.20 | ISP |
| Germall II | Propylparaben | 0.10 | ISP |
| | Diazolidinyl Urea | 0.25 | ISP-Sutton |
| Phase B | | | |
| Panethanol | Panethanol | 0.50 | N/A |

Procedure

1. Combine ingredients of Phase A in a ribbon type blender.
2. Pass through a micropulverizer until uniformly blended and mixed.
3. Add Phase B ingredient and blend well until evenly dispersed.