



MICRO POWDERS, INC. *Personal Care Division*

580 White Plains Road, Tarrytown, NY 10591 Tel: (914) 793-4058 Fax: (914) 472-7098 E-mail: mpi@micropowders.com

TALC FREE EYE SHADOW WITH SYNTHETIC DRY BINDERS

<u>Product Name</u>	<u>INCI Name</u>	<u>%W/W</u>	<u>Supplier</u>
Phase A			
Sericite PHN	Mica	79.45	Presperse LLC
Microease 110S	Synthetic Wax	3.00	Micro Powders, Inc.
Microslip 519	PTFE	1.80	Micro Powders, Inc.
Micropoly 220	Polyethylene	1.00	Micro Powders, Inc.
Microsilk 419	Polyethylene (&) PTFE 1	1.60	Micro Powders, Inc.
Phase B			
Red Iron Oxide 7080	Iron Oxide	4.00	Warner Jenkinson
Yellow Iron Oxide 7055	Iron Oxide	3.00	Warner Jenkinson
Black Iron Oxide 7133	Iron Oxide	2.00	Warner Jenkinson
Propylparaben, USP	Propylparaben	0.10	ISP
Methylparaben, USP	Methylparaben	0.30	ISP
Germall 115	Imidazolidinyl Urea	0.25	ISP
Phase C			
PEG-4 Dilaurate	PEG-4 Dilaurate	3.00	N/A
Liposorb TO	Sorbitan Trioleate	0.50	Lipo Chemicals

Procedure

1. Combine Phase A ingredients and blend.
2. Add Phase B ingredients in sequence and mill the entire batch to uniformity.
3. Pre-mix Phase C, spray into the batch and mix until uniform.
4. Mill the batch until there is no evidence of undispersed oil.
5. Press at 2000 psi in an appropriate container.