

Microspersion[®] 190-50

A nonionic water based dispersion of a unique, high performance composite of low density polyethylene and PTFE for maximum abrasion and burnish resistance with superior surface durability

Features and Benefits

.

- Convenient, ready-to-use, pourable nonionic wax dispersion
- High performance product for improving surface abrasion resistance and film toughness
- Synergistic wax combination that enhances PTFE mobility to the coating surface
- Low density polyethylene provides superior surface toughness, durability and mar resistance
- PTFE dramatically enhances abrasion resistance, antiblocking and film hardness

Dry Wax ID

Polyfluo 190

Recommended Addition Levels

2.0-5.0% (on total formula weight)

Systems and Applications

Water based coatings and inks. Industrial coatings (including plastic, metal, masonry and leather); architectural wall and trim paints; stains, sealers and varnishes; printing inks and OPV's (including flexo and gravure); coil coatings; rubber additives; floor coatings.

Typical Properties*

	Microspersion 190-50
Wax Solids	50%
Viscosity @ 25 °C (cP)	5,000 - 9,000
рН	9.0 - 10.5
Density @ 25 °C (g/cc)	1.00
Wax Mean Particle Size (µm)	9.0 - 12.0
NPIRI Grind	4.0 - 6.0

Mar-23

Micro Powders, Inc.

580 White Plains Road, Tarrytown, NY 10591 Tel: (914) 793-4058 | micropowders.com *The above data reflects typical properties. Please contact Micro Powders for official product specifications. The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.